

Hot Mounting Resins



- Complete product range
- High Quality
- Fast mounting
- Cost efficiency

NX MET Hot mounting resins selection:



	Standard	Standard +	Standard ++	Standard ++	Standard +++
Normal Mounting	Black Phenolic XPHB	Red, Green, Brown Phenolic XPHR, XPHG, XPHN	Glass Fiber Phenolic XGFB	D.phtalate Blue resin XDPB	Epoxy Black XEPB
Specific Mounting	Transparent Conductive XACT, XPHC	Transparent Conductive XACT, XPHC	Transparent Conductive XACT, XPHC	-- Conductive XPHC	-- Conductive XPHC
		Temperature	Heating time	Cooling time	
	XP serie, XGFB	150 to 180°C	3 to 5min	2 to 4min	
	XDPB, XEPB	160 to 180°C	5 to 6min	3 to 4min	
	XACT	180 to 190°C	7 to 9min	5 to 6min	

- **NX MET** resins are delivered in plastic bucket for 2.5 & 10kg packaging, and cardboard with plastic bag for 25Kg.



12, allée Pin de St Clair - 38130 Echirolles France

Tel : +33 438 49 28 33 Fax : +33 438 49 27 85

info@nxmet.com www.nxmet.com

Distributed by

